

# ATLAS

BUILDING PRODUCTS

A MARMON BERKSHIRE HATHAWAY COMPANY

PRODUCT SPECIFICATION SHEET

#10 ENDURAFast 410 STAINLESS STEEL™



**ASHLAND  
OHIO**

1628 TROY ROAD  
ASHLAND, OH 44805  
(800) 321-6977

**FLAT ROCK  
NORTH CAROLINA**

161 COMMERCIAL BLVD  
FLAT ROCK, NC 28731  
(828) 692-2603

**HOUSTON  
TEXAS**

4822 N. SAM HOUSTON PKWY W  
SUITE 100  
HOUSTON, TX 77086  
(800) 503-2105

**SALEM  
OREGON**

2655 TURNER ROAD  
SALEM, OR 97302  
(503) 362-1373

#10 ENDURAFAST 410 STAINLESS STEEL™



**Head**

1/4" hex head

**Thread**

Threads per inch: 14

**Point**

26 degree sharp point to penetrate quickly while minimizing chips

**Washer**

Bonded sealing washer

**Material**

410 stainless steel (magnetic)

**Finish**

Black E-Coating

SIZE	ITEM #	BOX QTY
10-14 x 1	89970BPN99AIPGY036	2,500
10-14 x 1-1/2	89971BPN99AIPGY036	2,500
10-14 x 2	89972BPN99AIPGY036	2,000

**STRENGTH CHARACTERISTICS**

MINIMUM TORSIONAL	MINIMUM TENSILE	MINIMUM SHEAR
68 in.-lbs.	1817 lbs.	1216 lbs.

**PULL OUT VALUES**

TEST MATERIAL	PENETRATION	VALUES
S-P-F #2	1"	498 lbs.
S-P-F #2	1-1/2"	899 lbs.
Hem Fir #2	1"	694 lbs.
Hem Fir #2	1-1/2"	1080 lbs.
1/2 CDX	FULL	361 lbs.
5/8 CDX	FULL	490 lbs.
3/4 CDX	FULL	560 lbs.

All test results and recommendations are based on laboratory tests. Specific job site conditions should be taken into consideration when specifying the proper fastener. Actual field values may vary, therefore we assume no liability for use of this information. Pull out values are a measurement of wood material strength. Use of impact style guns for installation not recommended.